

2/53NM

70%天丝

30%PBT

2/53NM

70%天丝

30%PBT

5701

白色

5705

亮黄

5709

皮粉

5713

灰紫

5717

粉色

5721

淡绿

5702

浅米

5706

浅绿

5710

浅桔

5714

兰紫

5718

桔粉

5722

兰色

5703

米色

5707

亮绿

5711

卡其

5715

浅紫

5719

大红

5723

上青

5704

浅黄

5708

绿色

5712

焦糖

5716



紫色

5720

酒红

5724

黑色



5715

浅紫

5716

紫色



5703

米色




5704

浅黄



707

绿色



708

绿色



5701



白色



5702

浅米









项目
(位)
/

测试方法

GB/T 4802.3-2008
起球箱法
起球14400转

≥ 3

3

测试结果

[样品识别]	测试方法	标准值及允差 (一等品)	检验检测结果	判定
●起球(级)	GB/T 4802.3-2008 起球箱法 起球14400转	≥3	3	符合
备注	<p>判定指标来源于客户要求的FZ/T 73005-2021。我单位获CMA及CAL认定授权的检验能力覆盖FZ/T 73005-2021所检项目。</p> <p>本报告中检验检测项目均在相应标准规定的环境条件下进行（有注明的除外）。 复印件、副本未重新加盖报告书确认章无效。 本报告检验检测地址为广州市番禺区珠江路1号。</p>			

签发: 钟菊祥 工程师

钟菊祥

——本报告

